



ORCHIDEE ROSE

Beerse HV - Softmud





ORCHIDEE ROSE

Beerse HV - Softmud

Product CE code	Format	Dimensions	Weight/piece	Pieces/m ²
153100-B1-1210	WF	± 215 l x 102 w x 50 h (mm)	± 1.83 kg	± 71
153110-B1-1210	WDF	± 215 l x 102 w x 65 h (mm)	± 2.39 kg	± 57
Size tolerance			T2	
Size range			R1	
Average gross dry density			1600 kg/m ³	
Average net dry density			1750 kg/m ³	
Density			D1	
Average compressive strength			≥ 12 N/mm ²	
Bond strength			0.15 N/mm ²	
Thermal conductivity			$\lambda_D = 0.47 \text{ W/m.k}$	
Water vapour permeability			$\mu = 5 / 10$	
Durability/frost resistance			F2	
Water absorption			≤ 17 %	
Active soluble salt content			S2	
Reaction to fire			A1	

06/08 This document does not imply a contract and substitutes all previous ones. The colours used in this datasheet show the natural tint of our bricks subject to the limitations of the printing process. The properties of bricks burnt of clay may vary, depending upon the works of origin and may slightly differ in colour from one production to another. Wienerberger reserves the right to alter the range and the technical data. Technical data are approximate.



Samples available upon request

Wienerberger Export Division

Kapel ter Bede 86
B-8500 Kortrijk
Belgium
Tel. +32 (0)56 26 43 45
Fax +32 (0)56 26 43 32
export.be@wienerberger.com
<http://export.wienerberger.com>