



Bromo

HANDMADE

Péruwelz

 **DESIMPEL**

Format	Dimensions	Weight kg/piece	Pieces/m ²
WFD	± 215 x 102,5 x 65 mm	± 2,37	± 58

Physical characteristics	
Waterabsorption Test performed on 10 pieces according to test method NBN B24-203	Maximum ≤ 14 %
Compressive strength Test performed on 10 pieces according to test method NBN B24-201 - §5.2	average compressive strength ≥ 15 N/mm ² characteristic compressive strength ≥ 10 N/mm ²
Efflorescence Test performed on 10 pieces according to test method NBN B24-209	no efflorescence
Hygrometric shrinkage and distension Test according to test method NBN B24-208	$E_f \leq 0,1 \text{ mm/m}$
Frost resistance Capillarity test according to test method NBN B27-010 Direct frost test according to test method NBN B27-009 and NBN B27-009 Add. 2 - Impregnation under 25,3 kPa	Gc ≤ -2,5 no frost damage
Class	very frost resistant

04/2004. This document does not imply a contract and substitutes all previous ones. The colours used in this datasheet show the natural tint of our bricks subject to the limitations of the printing process. The properties of bricks burnt of clay may vary, depending upon the works of origin and may slightly differ in colour from one production to another. Desimpel reserves the right to alter the range and the technical data. Technical data are approximate.